

ALTECH® PA66 A 1000/109 YL2492-12LS

Polyamide 66
ALBIS PLASTIC GmbH

Message:

ALTECH® PA66 A 1000/109 YL2492-12LS is a Polyamide 66 (Nylon 66) product. It is available in Asia Pacific, Europe, or North America.
Characteristics include:
Flame Rated
REACH Compliant
RoHS Compliant
Good Mold Release
Heat Stabilizer

General Information				
Additive		Heat Stabilizer		
Features		Good Mold Release		
		Heat Stabilized		
		High Flow		
		Laser Markable		
Agency Ratings		EC 1907/2006 (REACH)		
RoHS Compliance		RoHS Compliant		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.13	--	g/cm ³	ISO 1183
Water Absorption				ISO 62
Saturation, 23°C	8.5	--	%	
Equilibrium, 23°C, 50% RH	2.8	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	3300	1600	MPa	ISO 527-2
Tensile Stress (Yield)	80.0	--	MPa	ISO 527-2
Tensile Strain (Yield)	3.5	--	%	ISO 527-2
Flexural Stress	115	75.0	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength	4.0	--	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	50	1000	kJ/m ²	ISO 179/1eU
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	210	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	80.0	--	°C	ISO 75-2/A
Vicat Softening Temperature	200	--	°C	ISO 306/B50

Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	--	1.0E+3	ohms	IEC 60093
Volume Resistivity	1.0E+17	1.0E+12	ohms·cm	IEC 60093
Comparative Tracking Index	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
1.50 mm	V-2	--		
3.00 mm	V-2	--		
Injection	Dry	Unit		
Drying Temperature - Desiccant Dryer	80.0		°C	
Drying Time - Desiccant Dryer	2.0 to 12		hr	
Suggested Max Moisture	0.15		%	
Processing (Melt) Temp	270 to 290		°C	
Mold Temperature	40.0 to 80.0		°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

