Verolloy A2603

Acrylonitrile Butadiene Styrene + Nylon

PlastxWorld Inc.

Message:

Verolloy A2603 is an acrylonitrile butadiene styrene + nylon (ABS + nylon) product, which contains a 15% glass fiber reinforced material. It is available in North America or Europe.

Features include:

flame retardant/rated flame

high strength

Impact resistance

| General Information | | | | |
|-------------------------------------|-------------|---|--------------|-------------|
| Filler / Reinforcement | | Glass fiber reinforced material, 15% filler by weight | | |
| Features | | High tensile strength | | |
| | | Impact resistance, high | | |
| | | | | |
| Forms | | Particle | | |
| Physical | Dry | Conditioned | Unit | Test Method |
| Specific Gravity | 1.20 | | g/cm³ | ASTM D792 |
| Molding Shrinkage - Flow | 0.10 - 0.50 | | % | ASTM D955 |
| Water Absorption (24 hr) | 0.70 | | % | ASTM D570 |
| Hardness | Dry | Conditioned | Unit | Test Method |
| Rockwell Hardness | 116 | | | ASTM D785 |
| Mechanical | Dry | Conditioned | Unit | Test Method |
| Tensile Strength (Break) | 82.7 | 62.1 | МРа | ASTM D638 |
| Tensile Elongation (Break) | 6.0 | 7.0 | % | ASTM D638 |
| Flexural Modulus | 4270 | 3240 | MPa | ASTM D790 |
| Flexural Strength | 117 | 96.5 | МРа | ASTM D790 |
| Impact | Dry | Conditioned | Unit | Test Method |
| Notched Izod Impact | | | | ASTM D256 |
| | | 170 | J/m | ASTM D256 |
| 23°C, 3.18 mm | 140 | | J/m | ASTM D256 |
| Thermal | Dry | Conditioned | Unit | Test Method |
| Deflection Temperature | | | | |
| Under Load (1.8 MPa, Unannealed) | 165 | 150 | °C | ASTM D648 |
| Flammability | Dry | Conditioned | - | Test Method |
| Flame Rating (1.50 mm) | HB | | | UL 94 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

