

# FHR Polypropylene P4C5T-013

Polypropylene Homopolymer

Flint Hills Resources, LP

Message:

FHR Polypropylene P4C5T-013 is a polypropylene homopolymer (PP Homopoly) product. It can be processed by injection molding and is available in North America. The application areas of FHR Polypropylene P4C5T-013 include packaging, home application, food contact application and medical/health care.

- Features include:
- flame retardant/rated flame
  - Good processability
  - Homopolymer
  - Antistatic

General Information			
UL YellowCard	E336707-100613148		
Additive	Antistatic property		
Features	Homopolymer		
	Antistatic property		
	Workability, good		
	No kinetic components		
Uses	Household goods		
	Hard packaging		
Agency Ratings	DMF not rated		
	FDA 21 CFR 177.1520(c) 1.1a		
RoHS Compliance	Contact manufacturer		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	20	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	105		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	34.0	MPa	ASTM D638
Tensile Elongation (Yield)	9.0	%	ASTM D638
Flexural Modulus - 1% Secant	1240	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	20	J/m	ASTM D256
Dart Drop Impact (23°C)	6.00	J	ASTM D5420

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	93.0	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Additional Information			

Notice regarding medical applications: This Flint Hills product meets certain requirements for use in medical applications. It is the responsibility of the medical device or pharmaceutical manufacturer to determine that this Flint Hills product is safe, lawful and technically suitable for the intended use. Flint Hills encourages its customers to review their application with a Flint Hills technical representative to ensure that this product is not used in ways for which it was not intended or tested. Flint Hills makes no warranties (express or implied), promises or guarantees concerning the suitability of this product for use in any given medical application. Not intended for use in the manufacture of any form of implanted medical or surgical device.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

