

Leona™ FG173

Polyamide 66

Asahi Kasei Chemicals Corporation

Message:

Leona™ FG173 is a Polyamide 66 (Nylon 66) product filled with glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, or North America.
Typical application: Electrical/Electronic Applications.
Characteristics include:
Flame Rated
Flame Retardant
Heat Stabilizer

General Information	
UL YellowCard	E48285-240907
Filler / Reinforcement	Glass Fiber
Additive	Flame Retardant
	Heat Stabilizer
Features	Flame Retardant
	Halogenated
	Heat Stabilized
Uses	Connectors
	Electrical Parts
	Electrical/Electronic Applications
	Switches

Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.65	--	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage				Internal Method
Across Flow	0.70	--	%	
Flow	0.30	--	%	
Water Absorption				
Saturation, 23°C	--	0.80	%	
Equilibrium, 23°C, 50% RH	--	0.80	%	ISO 62
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness (M-Scale)	100	60		ASTM D785, ISO 2039-2
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	11700	10500	MPa	ISO 527-2
Tensile Stress				
Break, 23°C	174	137	MPa	ISO 527-2

--	167	142	MPa	ASTM D638
Tensile Elongation				
Break	2.5	3.5	%	ASTM D638
Break, 23°C	2.0	2.0	%	ISO 527-2
Flexural Modulus				
--	10800	8300	MPa	ASTM D790
23°C	10300	8700	MPa	ISO 178
Flexural Strength				
--	250	221	MPa	ASTM D790
23°C	259	188	MPa	ISO 178
Taber Abrasion Resistance (1000 Cycles)	--	29.0	mg	ASTM D1044
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength	11	10	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	50	52	kJ/m ²	ISO 179
Notched Izod Impact	88	98	J/m	ASTM D256
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				
0.45 MPa, Unannealed	260	--	°C	ASTM D648
0.45 MPa, Unannealed	262	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	252	--	°C	ASTM D648
1.8 MPa, Unannealed	245	--	°C	ISO 75-2/A
CLTE - Flow	3.0E-5	--	cm/cm/°C	ASTM D696
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+14	--	ohms	ASTM D257, IEC 60093
Volume Resistivity				
--	1.0E+15	--	ohms·cm	ASTM D257
23°C	1.0E+15	--	ohms·cm	IEC 60093
Dielectric Strength	28	--	kV/mm	ASTM D149, IEC 60243-1
Comparative Tracking Index (3.00 mm)	275	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (0.750 mm)	V-0	--		UL 94
Glow Wire Flammability Index (3.00 mm)	960	--	°C	IEC 60695-2-12

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

