

Aegis® H155QP

Polyamide 6

Honeywell

Message:

Aegis® H155QP is a lubricated, high viscosity nylon 6 extrusion grade homopolymer for cast or blown film. It conforms to FDA requirements of 21 CFR 177.1500 as well as EU Directive 2002/72/EC. It possesses the combination of strength, toughness and thermoforming properties associated with nylon 6 as well as excellent heat, chemical, and abrasion resistance.

General Information	
Additive	Lubricant
Features	Homopolymer
	Good strength
	Good wear resistance
	Good chemical resistance
	Heat resistance, high
	Good toughness
	Lubrication
	Viscosity, High
Uses	Packaging
	cast film
Agency Ratings	FDA 21 CFR 177.1500
	European 2002/72/EC
Forms	Particle
Processing Method	Blow film
	Extrusion
	cast film
	Thermoforming

Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (235°C/1.0 kg)	1.1	g/10 min	ASTM D1238
Water Absorption			ASTM D570
24 hr	1.6	%	ASTM D570
Saturation	9.5	%	ASTM D570
Balance	2.7	%	ASTM D570
Moisture Content		%	
Films	Nominal Value	Unit	Test Method
Carbon Dioxide Transmission Rate (23°C)	72.8	cm ³ /m ² /24 hr	ASTM D1434

Nitrogen Transmission Rate (23°C)	14.0	cm ³ /m ² /24 hr	ASTM D1434
Oxygen Transmission Rate (23°C)	40	cm ³ /m ² /24 hr	ASTM D3985
Thermal	Nominal Value	Unit	
Melting Temperature	220	°C	
Additional Information			

FAV, ASTM D789: 15596% SAV: 4.0Extractible Content: 0.7 %

Extrusion	Nominal Value	Unit
Drying Temperature	80.0	°C
Cylinder Zone 1 Temp.	230 - 260	°C
Cylinder Zone 2 Temp.	230 - 260	°C
Cylinder Zone 3 Temp.	230 - 260	°C
Cylinder Zone 4 Temp.	230 - 260	°C
Cylinder Zone 5 Temp.	230 - 260	°C
Adapter Temperature	260 - 266	°C
Melt Temperature	260 - 270	°C
Die Temperature	260	°C

Extrusion instructions

The values listed above in Extrusion are for cast film. Typical Barrel Profile for Tubular (Blown) Films:

Barrel Temperature: 246 to 254°C (474 to 490°F)

Adapter Temperature: 260°C (500°F)

Die Temperature: 254°C (490°F)

Processing Melt Temperature: 254 to 260°C (490 to 500°F)

Screw Parameters:

Metering section: 40%

Transition section: 3 to 4 flights

Feed section balance of screw length

Compression ratio: 3.5:1 to 4.0:1

L/D ratio: 24:1

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT