

CERTENE™ 8320

Linear Low Density Polyethylene
Muehlstein

Message:

CERTENE™8320 is a linear low density polyethylene material. This product is available in North America.

General Information			
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.924	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	20	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (50°C, 100% Igepal, F50)	20.0	hr	ASTM D1693
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	50		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	11.7	MPa	ASTM D638
Fracture	7.58	MPa	ASTM D638
Tensile Elongation			ASTM D638
Yield	3.0	%	ASTM D638
Fracture	60	%	ASTM D638
Flexural Modulus - 2% Secant	386	MPa	ASTM D790B
Impact	Nominal Value	Unit	Test Method
Tensile Impact Strength ¹	168	kJ/m ²	ASTM D1822
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	42.8	°C	ASTM D648
Brittleness Temperature	< -76.1	°C	ASTM D746
Vicat Softening Temperature	93.9	°C	ASTM D1525
Melting Temperature (DSC)	123	°C	Internal method
Peak Crystallization Temperature (DSC)	108	°C	Internal method
Additional Information			
根据 ASTM D 4976 进行基板模制和测试.			
NOTE			
1.	Type s		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

