ENSOFT SL-560-55A

Thermoplastic Elastomer

ENPLAST, a Ravago Group Company

Message:

ENSOFT SL-560-55A is a thermoplastic elastomer (TPE) product. It can be processed by extrusion or injection molding and is available in North America or Europe.

Features include:

Flame Retardant

Good UV resistance

General Information			
Features	Good UV resistance		
	Ozone resistance		
	Flame retardancy		
Forms	Particle		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.16	g/cm³	ISO 1183
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	55		ISO 868
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ISO 37
100% strain	1.20	MPa	ISO 37
300% strain	2.50	MPa	ISO 37
Tensile Stress (Break)	7.20	MPa	ISO 37
Tensile Elongation (Break)	600	%	ISO 37
Additional Information			
The value listed as Density, ISO 1183, v	was tested in accordance with ISO 27	781.Ozone Resistance, ISO 1431: N	o Crack
Injection	Nominal Value	Unit	
Rear Temperature	150 - 160	°C	
Front Temperature	170 - 180	°C	
Nozzle Temperature	185 - 190	°C	
Processing (Melt) Temp	190 - 200	°C	
Mold Temperature	10.0 - 50.0	°C	
Screw L/D Ratio	20.0:1.0		
Screw Compression Ratio	2.5:1.0		
Extrusion	Nominal Value	Unit	
Drying Temperature	90.0	°C	

Drying Time	1.0	hr	
Cylinder Zone 1 Temp.	170	°C	
Cylinder Zone 2 Temp.	180	°C	
Cylinder Zone 3 Temp.	190	°C	
Cylinder Zone 4 Temp.	195	°C	
Cylinder Zone 5 Temp.	200	°C	
Extrusion instructions			

Machine Capacity, 30 mm cylinder diameter: 15 to 20 kg/hrMachine Capacity, 45 mm cylinder diameter: 60 to 85 kg/hrMachine Capacity, 60 mm cylinder diameter: 100 to 150 kg/hrMachine Capacity, 90 mm cylinder diameter: 225 to 300 kg/hr

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

