# MBA PS 3123

### General Purpose Polystyrene

#### **MBA** Polymers

#### Message:

A post-consumer recycled impact modified polystyrene for general use. Available in standard grey (reference 70/15) and standard black (reference 90/04). Other colors may be available upon request.

| General Information                      |                        |          |              |
|--|------------------------|----------|--------------|
| Additive                                 | Impact Modifier        |          |              |
| Recycled Content                         | Yes                    |          |              |
| Features                                 | Good Impact Resistance |          |              |
| Uses                                     | General Purpose        |          |              |
| Appearance                               | Black                  |          |              |
|  | Colors Available       |          |              |
|  | Grey                   |          |              |
|  |                        |          |              |
| Forms                                    | Pellets                |          |              |
| Processing Method                        | Extrusion              |          |              |
|  | Injection Molding      |          |              |
|  |                        |          |              |
| Physical                                 | Nominal Value          | Unit     | Test Method  |
| Density                                  | 1.05                   | g/cm³    | ISO 1183     |
| Melt Mass-Flow Rate (MFR) (200°C/5.0 kg) | 6.5                    | g/10 min | ISO 1133     |
| Mechanical                               | Nominal Value          | Unit     | Test Method  |
| Tensile Stress (Yield, 23°C)             | 25.0                   | MPa      | ISO 527-2/50 |
| Impact                                   | Nominal Value          | Unit     | Test Method  |
| Notched Izod Impact Strength (23°C)      | 8.0                    | kJ/m²    | ISO 180/1A   |
| Injection                                | Nominal Value          | Unit     |              |
| Drying Temperature                       | 70.0                   | °C       |              |
| Drying Time                              | 1.0 to 2.0             | hr       |              |
| Suggested Max Moisture                   | 0.050 to 0.10          | %        |              |
| Processing (Melt) Temp                   | 190 to 230             | °C       |              |
| Mold Temperature                         | 20.0 to 60.0           | °C       |              |
| Extrusion                                | Nominal Value          | Unit     |              |
| Drying Temperature                       | 70.0                   | °C       |              |
| Drying Time                              | 1.0 to 2.0             | hr       |              |
| Suggested Max Moisture                   | 0.050 to 0.10          | %        |              |
| Melt Temperature                         | 180 to 210             | °C       |              |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

