

AEI TP-0832

Polyethylene
AEI Compounds Limited

Message:

Thermoplastic, low smoke, halogen free, flame retardant compound for cable insulation and sheathing.

This is a flame retardant, low smoke, thermoplastic compound which has been specially developed to meet the requirements of limited toxic and corrosive fume emission, having good moisture resistance and hot pressure performance.

TP-0832 has been specially developed to comply with the requirements of BS7655 Section 6 for types LTS1, 2, 3 and 4; EN 50290-2-27 for type HM2 and HD 604 for type HM4. Cables sheathed with TP-0832 have received LPCB approval.

TP-0832 is available in the following versions:

TP-0832N (natural colour)

TP-0832B (coloured black)

TP-0832NU (with a non-staining UV stabiliser added)

TP-0832BU (carbon black added to give UV stability)

General Information			
Additive	Flame retardancy		
Features	Low smoke		
	Moisture resistance		
	Halogen-free		
	Flame retardancy		
Uses	Flame Retardant Insulation		
	Flame Retardant Jacketing		
	Cable sheath		
	Wire and cable applications		
Agency Ratings	BS 7655 LTS1-2-3-4		
	EC 1907/2006 (REACH)		
	EN 50290-2-27		
	HD 604		
RoHS Compliance	RoHS compliance		
Forms	Particle		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	1.48	g/cm ³	BS 2782 620A
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	90		
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	15.5	MPa	IEC 60811-1-1
Tensile Strain			
Fracture	170	%	IEC 60811-1-1

Fracture, -30°C ¹	60	%	IEC 60811-1-4
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength			IEC 60811-1-2
70°C, 168 hr, in water	-15	%	IEC 60811-1-2
100°C, 168 hr	-10	%	IEC 60811-1-2
Change in Tensile Strain at Break			IEC 60811-1-2
70°C, 168 hr, in water	15	%	IEC 60811-1-2
100°C, 168 hr	15	%	IEC 60811-1-2
Thermal	Nominal Value	Unit	Test Method
Deformation			IEC 60811-3-1
90°C	25	%	IEC 60811-3-1
100°C	30	%	IEC 60811-3-1
Cold shock (-30°C)	pass		IEC 60811-1-4
Cold bending (-30°C)	pass		IEC 60811-1-4
Heat-resistant stress cracking (80°C)	pass		Internal method
Temperature index	270	°C	ISO 4589-3
Conduction rate-of gases	2.10	μS/cm	EN 50267-2-3
Corrosive gases in flue gas-pH	5.80		EN 50267-2-3
Smoke	75	%	
Halogen Acid Gas Evolution		%	IEC 60754-1
Tear Strength	8	N/mm	BS 6469
Head Temperature	160	°C	
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	32	%	ISO 4589-2
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	120	°C	
Cylinder Zone 2 Temp.	130	°C	
Cylinder Zone 3 Temp.	140	°C	
Cylinder Zone 4 Temp.	150	°C	
Melt Temperature	< 170	°C	
Die Temperature	160	°C	
Extrusion instructions			
An extruder with an L/D ratio (length/diameter) of 15-24 and an extruder screw with a compression ratio 1.5:1 or less are recommended.			
NOTE			
1.	pass		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

