

Luran® S 757R

Acrylonitrile Styrene Acrylate
Styrolution

Message:

Luran S 757R is a general injection molding grade with enhanced stiffness.

General Information			
UL YellowCard	E108538-100840261		
Features	Good Chemical Resistance		
	Good Stiffness		
Uses	Household Goods		
	Windows & Doors		
Forms	Pellets		
Processing Method	Injection Molding		
Multi-Point Data	Creep Modulus vs. Time (ISO 11403-1)		
	Isochronous Stress vs. Strain (ISO 11403-1)		
	Isothermal Stress vs. Strain (ISO 11403-1)		
	Secant Modulus vs. Strain (ISO 11403-1)		
	Viscosity vs. Shear Rate (ISO 11403-2)		
Physical	Nominal Value	Unit	Test Method
Density	1.07	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	8.00	cm³/10min	ISO 1133
Water Absorption			ISO 62
Saturation, 23°C	1.7	%	
Equilibrium, 23°C, 50% RH	0.35	%	
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	100	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2600	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	56.0	MPa	ISO 527-2
Tensile Strain (Yield, 23°C)	3.1	%	ISO 527-2
Tensile Creep Modulus (1000 hr)	1400	MPa	ISO 899-1
Flexural Stress	80.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-30°C	3.0	kJ/m²	

23°C	12	kJ/m ²	
Notched Izod Impact Strength			ISO 180/A
-30°C	3.0	kJ/m ²	
23°C	13	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	101	°C	ISO 75-2/B
1.8 MPa, Unannealed	97.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	105	°C	ISO 306/A50
--	98.0	°C	ISO 306/B50
CLTE - Flow	8.0E-5 to 1.1E-4	cm/cm/°C	ISO 11359-2
Thermal Conductivity	0.17	W/m/K	DIN 52612
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13	ohms	IEC 60093
Volume Resistivity	1.0E+14	ohms·cm	IEC 60093
Dielectric Constant			IEC 60250
100 Hz	3.70		
1.00 mm, 1 MHz	3.40		
Dissipation Factor			IEC 60250
100 Hz	9.0E-3		
1 MHz	0.025		
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 to 4.0	hr	
Processing (Melt) Temp	240 to 280	°C	
Mold Temperature	60.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT