

VITAMIDE® AT37NT6314

Polyamide 66

Jackdaw Polymers

Message:

VITAMIDE® AT37NT6314 is a Polyamide 66 (Nylon 66) product filled with 33% glass fiber. It is available in Europe. Primary characteristic: flame rated.

General Information			
Filler / Reinforcement	Glass Fiber,33% Filler by Weight		
Appearance	Natural Color		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.39	g/cm ³	ASTM D792, ISO 1183
Water Absorption (23°C, 24 hr)	1.0	%	ASTM D570, ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	130	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break)	4.0	%	ASTM D638, ISO 527-2
Flexural Modulus	7500	MPa	ASTM D790, ISO 178
Flexural Stress			
--	200	MPa	ISO 178
Break	200	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	16	kJ/m ²	ISO 179
Charpy Notched Impact Strength ¹	16.0	kJ/m ²	ASTM D256
Charpy Unnotched Impact Strength ²	78.0	kJ/m ²	ASTM D256
Charpy Unnotched Impact Strength	78	kJ/m ²	ISO 179
Notched Izod Impact Strength	15	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	250	°C	ASTM D648, ISO 75-2/B
1.8 MPa, Unannealed	240	°C	ASTM D648, ISO 75-2/A
Melting Temperature	260	°C	ASTM D2117, ISO 1218
CLTE - Flow	2.4E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms · cm	ASTM D257, IEC 60093
Dielectric Strength	34	kV/mm	ASTM D149, IEC 60243-1
Comparative Tracking Index			
Solution A	450	V	IEC 60112
-- ³	450	V	ASTM D3638
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Oxygen Index	23	%	ASTM D2863, ISO 4589-2

NOTE	
1.	Method B
2.	Method A
3.	Solution A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT