

# Hifax TSOP EM1 G63083

Polypropylene Impact Copolymer

LyondellBasell Industries

## Message:

Hifax TSOP EM1 G63083 is a mineral filled high impact polypropylene copolymer. The grade has been specifically designed for moulding large complex parts that require high impact as well as good stiffness.

General Information			
Filler / Reinforcement	Mineral		
Features	Good Processability		
	Good Stiffness		
	High Flow		
	High Impact Resistance		
	Impact Copolymer		
	Paintable		
Uses	Automotive Bumper		
	Automotive Exterior Parts		
	Automotive Interior Parts		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	0.975	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	27	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	> 58		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	17.0	MPa	ISO 527-2/50
Tensile Strain (Break, 23°C)	> 100	%	ISO 527-2/50
Flexural Modulus <sup>1</sup> (23°C)	1200	MPa	ISO 178
Flexural Stress (23°C)	21.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ISO 180/1A
-30°C	> 6.0	kJ/m <sup>2</sup>	
23°C	> 40	kJ/m <sup>2</sup>	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	> 95.0	°C	ISO 75-2/B
NOTE			
1.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

