

# 4TECH® 9KY22120 HUV

Polybutylene Terephthalate + ASA

4Plas

Message:

4TECH 9KY22120 HUV is a Standard Flow 20% Glass Fibre Reinforced Heat & UV Stabilised PBT / ASA Blend

| General Information                                       |                                                       |                   |             |
|-----------------------------------------------------------|-------------------------------------------------------|-------------------|-------------|
| Filler / Reinforcement                                    | Glass fiber reinforced material, 20% filler by weight |                   |             |
| Additive                                                  | heat stabilizer                                       |                   |             |
|                                                           | UV stabilizer                                         |                   |             |
| Features                                                  | Good UV resistance                                    |                   |             |
|                                                           | Thermal Stability                                     |                   |             |
| Processing Method                                         | Injection molding                                     |                   |             |
| Physical                                                  | Nominal Value                                         | Unit              | Test Method |
| Density                                                   | 1.35                                                  | g/cm <sup>3</sup> | ISO 1183    |
| Molding Shrinkage                                         |                                                       |                   |             |
| Vertical flow direction                                   | 0.70                                                  | %                 |             |
| Flow direction                                            | 0.40                                                  | %                 |             |
| Water Absorption <sup>1</sup> (Equilibrium, 23°C, 50% RH) | 0.20                                                  | %                 | ISO 62      |
| Moisture Content                                          | < 800                                                 | ppm               | ISO 960     |
| Mechanical                                                | Nominal Value                                         | Unit              | Test Method |
| Tensile Modulus (23°C)                                    | 7000                                                  | MPa               | ISO 527-2/5 |
| Tensile Stress (Break, 23°C)                              | 110                                                   | MPa               | ISO 527-2/5 |
| Tensile Strain (Break, 23°C)                              | 3.0                                                   | %                 | ISO 527-2/5 |
| Impact                                                    | Nominal Value                                         | Unit              | Test Method |
| Notched Izod Impact                                       |                                                       |                   | ISO 180/1A  |
| -30°C                                                     | 8.0                                                   | kJ/m <sup>2</sup> | ISO 180/1A  |
| 23°C                                                      | 9.0                                                   | kJ/m <sup>2</sup> | ISO 180/1A  |
| Thermal                                                   | Nominal Value                                         | Unit              | Test Method |
| Heat Deflection Temperature                               |                                                       |                   |             |
| 0.45 MPa, not annealed                                    | 215                                                   | °C                | ISO 75-2/B  |
| 1.8 MPa, not annealed                                     | 175                                                   | °C                | ISO 75-2/A  |
| Melting Temperature <sup>2</sup>                          | 225                                                   | °C                | ISO 11357   |
| Electrical                                                | Nominal Value                                         | Unit              | Test Method |
| Surface Resistivity                                       | 1.0E+14                                               | ohms              | IEC 60093   |
| Volume Resistivity                                        | 1.0E+16                                               | ohms · cm         | IEC 60093   |
| Flammability                                              | Nominal Value                                         | Unit              | Test Method |

| Flame Rating                                           |               | UL 94 |
|--------------------------------------------------------|---------------|-------|
| 0.750 mm                                               | HB            | UL 94 |
| 1.60 mm                                                | HB            | UL 94 |
| Injection                                              | Nominal Value | Unit  |
| Drying Temperature                                     | 120           | °C    |
| Drying Time                                            | 2.0 - 4.0     | hr    |
| Suggested Max Moisture                                 | 0.020         | %     |
| Processing (Melt) Temp                                 | 240 - 280     | °C    |
| Mold Temperature                                       | 50.0 - 110    | °C    |
| Injection Rate                                         | Fast          |       |
| Holding Pressure                                       | 40.0 - 80.0   | MPa   |
| Screw Speed                                            | 200           | rpm   |
| Injection instructions                                 |               |       |
| Feed Throat Temperature: 50 - 70 °C Back Pressure: Low |               |       |
| NOTE                                                   |               |       |
| 1.                                                     | 24 Hrs        |       |
| 2.                                                     | 10 K/min      |       |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

