

Matrixx 14N6020

Polypropylene
The Matrixx Group, Inc.

Message:

Matrixx 14N6020 is a polypropylene material. This product is available in North America.
The main features of the Matrixx 14N6020 are:
flame retardant/rated flame
Flame Retardant

General Information			
Additive	Flame retardancy		
Features	Low blur phenomenon		
	Flame retardancy		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.988	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	18	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.6 - 2.2	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	34.5	MPa	ASTM D638
Flexural Modulus	1450	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	27	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	96.1	°C	ASTM D648
RTI Elec	65.0	°C	UL 746
RTI Imp	65.0	°C	UL 746
RTI	65.0	°C	UL 746
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	V-0		UL 94
Additional Information			

The value listed as Mold Shrinkage, ASTM D955, was tested in accordance with Matrixx test methods.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

