

Geon™ HTX Ultra LA426 Gray 2382

Polyvinyl Chloride Alloy

PolyOne Corporation

Message:

It is most suitable for black and darker colors with color values between 50 and 70L. The same applies to colors with color values above 70L.

General Information			
UL YellowCard	E41877-100465201		
Features	Rigidity, high		
	Impact resistance, high		
Uses	Outdoor application		
	Profile		
Forms	Particle		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.25	g/cm ³	ASTM D792
PVC Cell Classification	4-41410-64-0000		ASTM D4216
PVC Cell Classification	15215		ASTM D1784
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 15 sec)	75		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	1900	MPa	ASTM D638
Tensile Strength ² (Yield)	35.2	MPa	ASTM D638
Flexural Modulus	1910	MPa	ASTM D790
Flexural Strength	61.9	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm, Compression Molded)	720	J/m	ASTM D256A
Drop Impact Resistance			ASTM D4226
23°C ³	59.6	J/cm	ASTM D4226
23°C ⁴	178	J/cm	ASTM D4226
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, unannealed, 3.18mm	90.0	°C	ASTM D648
0.45 MPa, annealed, 3.18mm	91.1	°C	ASTM D648
1.8 MPa, unannealed, 3.18mm	83.3	°C	ASTM D648
1.8 MPa, annealed, 3.18mm	86.7	°C	ASTM D648
CLTE - Flow	8.4E-5	cm/cm/°C	ASTM D696

Additional Information		Nominal Value
Ease of Sizing		Acceptable
推荐在华氏160度下将材料干燥至少2小时.物理属性基于 Geon HTX Ultra LA426 Gray 2382		
Extrusion	Nominal Value	Unit
Melt Temperature	174 - 193	°C
NOTE		
1.	Type 1, 5.1 mm/min	
2.	Type 1, 5.1 mm/min	
3.	Procedure A, C.125 Throwing	
4.	Procedure B, C.125 Throwing	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

