

Razamid® A111U

Polyamide 66

Razin™ Engineering Plastics

Message:

Razamid A111U is an Injection grade Impact modified natural color polyamide 66. It combines good strength, stiffness and toughness as well as excellent heat, chemical and abrasion resistance.

General Information			
Additive	Impact Modifier		
Features	Good Abrasion Resistance		
	Good Chemical Resistance		
	Good Stiffness		
	Good Strength		
	Good Toughness		
	High Heat Resistance		
	High Impact Resistance		
	Impact Modified		
Appearance	Natural Color		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.80	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	45.0	MPa	ASTM D638
Tensile Elongation (Break)	50	%	ASTM D638
Flexural Modulus	1800	MPa	ASTM D790
Flexural Strength	65.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	No Break		ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	215	°C	
1.8 MPa, Unannealed	80.0	°C	
Vicat Softening Temperature	225	°C	ASTM D1525
Peak Melting Temperature	250	°C	ASTM D3418
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+12	ohms	IEC 60093
Volume Resistivity	1.0E+13	ohms · cm	IEC 60093
Dielectric Strength	20	kV/mm	ASTM D149

Injection	Nominal Value	Unit
Drying Temperature	90.0 to 110	°C
Drying Time	2.0 to 4.0	hr
Rear Temperature	260 to 280	°C
Middle Temperature	265 to 300	°C
Front Temperature	275 to 305	°C
Processing (Melt) Temp	275 to 310	°C
Mold Temperature	50.0 to 80.0	°C
Injection Pressure	55.0 to 140	MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

