

Durethan® BKV 130 DUS008 901510

Polyamide 6

LANXESS GmbH

Message:

PA 6, 30 % glass fibers, injection molding, improved impact strength

General Information				
UL YellowCard		E245249-100868023		
Filler / Reinforcement		Glass Fiber,30% Filler by Weight		
Features		Good Impact Resistance		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.37	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 2577
Across Flow : 280°C, 2.00 mm ¹	0.70	--	%	
Across Flow : 120°C, 4 hr, 2.00 mm ²	0.20	--	%	
Flow : 280°C, 2.00 mm ³	0.30	--	%	
Flow : 120°C, 4 hr, 2.00 mm ⁴	0.10	--	%	
Water Absorption				ISO 62
Saturation, 23°C	6.3	--	%	
Equilibrium, 23°C, 50% RH	1.9	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	9300	5200	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	155	95.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	3.5	7.5	%	ISO 527-2/5
Flexural Modulus ⁵ (23°C)	8600	4700	MPa	ISO 178/A
Flexural Stress				ISO 178/A
3.5% Strain,23°C	240	135	MPa	
23°C ⁶	245	160	MPa	
Flexural Strain at Flexural Strength ⁷ (23°C)	4.0	6.3	%	ISO 178/A
ISO Shortname	PA 6-HI, GR, 14-090, GF30	--		ISO 1874
Residual Moisture Content	0.030 to 0.12		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	70	75	kJ/m ²	
23°C	90	90	kJ/m ²	

Notched Izod Impact Strength				ISO 180/1A
-30°C	< 10	< 10	kJ/m ²	
23°C	12	20	kJ/m ²	
Unnotched Izod Impact Strength				ISO 180/1U
-30°C	70	70	kJ/m ²	
23°C	80	85	kJ/m ²	
Multi-Axial Instrumented Impact Energy				ISO 6603-2
-30°C	2.60	--	J	
23°C	4.00	--	J	
Multi-Axial Instrumented Impact Peak Force				ISO 6603-2
-30°C	750	--	N	
23°C	930	--	N	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	220	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	205	--	°C	ISO 75-2/A
Vicat Softening Temperature	213	--	°C	ISO 306/B120
Melting Temperature ⁸	222	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow : 23 to 55°C	2.0E-5	--	cm/cm/°C	
Transverse : 23 to 55°C	1.0E-4	--	cm/cm/°C	
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 to 6.0		hr	
Processing (Melt) Temp	260 to 290		°C	
Mold Temperature	80.0 to 100		°C	
NOTE				
1.	60x60x2mm, 80°C MT, 600 bar			
2.	60x60x2mm			
3.	60x60x2mm, 80°C MT, 600 bar			
4.	60x60x2mm			
5.	2.0 mm/min			
6.	2.0 mm/min			
7.	2 mm/min			
8.	10°C/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

