

TRANSMARE® 35HT20-0.001

Polypropylene Homopolymer

Transmare Compounding B.V.

Message:

TRANSMARE® 35HT20-0.001 is a 20% fine white talc filled polypropylene homopolymer. It combines a high stiffness with very good flow properties. Suitable for (light) coloring. This grade contains an anti static agent.

General Information			
Filler / Reinforcement	Talc,20% Filler by Volume		
Additive	Antistatic		
Features	Antistatic		
	Good Flow		
	High Stiffness		
	Homopolymer		
	Recyclable Material		
Appearance	White		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.05	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	25	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	72		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (4.00 mm)	3000	MPa	ISO 527-2/1
Tensile Stress			ISO 527-2/50
Yield, 4.00 mm	35.0	MPa	
Break, 4.00 mm	22.0	MPa	
Tensile Strain			ISO 527-2/50
Yield, 4.00 mm	4.4	%	
Break, 4.00 mm	12	%	
Flexural Modulus	2900	MPa	ISO 178
Flexural Stress	55.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1A
-40°C	1.0	kJ/m ²	
23°C	2.0	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1U
-40°C	13	kJ/m ²	

23°C	30	kJ/m ²	
Notched Izod Impact Strength			ISO 180/1A
-40°C	2.1	kJ/m ²	
23°C	2.2	kJ/m ²	
Unnotched Izod Impact Strength			ISO 180/1U
-40°C	13	kJ/m ²	
23°C	25	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	110	°C	ISO 75-2/B
1.8 MPa, Unannealed	60.0	°C	ISO 75-2/A
Vicat Softening Temperature	155	°C	ISO 306/A
Injection	Nominal Value	Unit	
Suggested Max Moisture	< 0.20	%	
Rear Temperature	170	°C	
Middle Temperature	230	°C	
Front Temperature	240	°C	
Nozzle Temperature	250	°C	
Mold Temperature	40.0 to 60.0	°C	
Injection Rate	Moderate-Fast		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

