# Kepamid® 2313GFS

# Polyamide 66

### Korea Engineering Plastics Co., Ltd

#### Message:

Kepamid® 2313GFS is a Polyamide 66 (Nylon 66) material filled with 13% glass fiber. It is available in Asia Pacific, Europe, or North America. Important attributes of Kepamid® 2313GFS are: Flame Rated Impact Resistant Typical applications include: Automotive Electrical/Electronic Applications

General Information						
UL YellowCard	E120354-220471	E120354-220471				
Filler / Reinforcement	Glass Fiber,13% Filler by	Glass Fiber,13% Filler by Weight				
Features	Good Impact Resistance	Good Impact Resistance				
Jses Automotive Applications						
	Electrical/Electronic Appl	Electrical/Electronic Applications				
Forms	Pellets					
Physical	Nominal Value	Unit	Test Method			
Specific Gravity	1.19	g/cm³	ASTM D792			
Melt Mass-Flow Rate (MFR) (275°C/2.16						
kg)	8.0	g/10 min	ASTM D1238			
Mechanical	Nominal Value	Unit	Test Method			

Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	74.5	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	3.3	%	ASTM D638
Flexural Modulus (23°C)	3920	MPa	ASTM D790
Flexural Strength (Yield, 23°C)	123	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	98	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	260	°C	DSC
Flammability	Nominal Value		Test Method
Flame Rating (0.800 mm)	НВ		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

