

Honeywell PMP R1500

Polymethylpentene

Honeywell

Message:

The Honeywell R-Series PMP film is made from polymethylpentene. It provides more toughness and heat resistance than standard polyolefins for release film applications. R-Series Film is available in the following colors: Blue and Clear.

General Information			
Features	Heat resistance, medium		
	Good toughness		
Uses	release film		
Appearance	Blue		
	Clear/transparent		
Forms	Films		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.908	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Coefficient of Friction			ASTM D1894
With Metal-Dynamic	0.55		ASTM D1894
With self-dynamics	1.0		ASTM D1894
Films	Nominal Value	Unit	Test Method
secant modulus			ASTM D882
MD	665	MPa	ASTM D882
TD	707	MPa	ASTM D882
Tensile Strength			ASTM D882
MD: Yield	36.9	MPa	ASTM D882
TD: Fracture	30.3	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Fracture	250	%	ASTM D882
TD: Fracture	350	%	ASTM D882
Water Vapor Transmission	60	g/m ² /24 hr	ASTM E96
Additional Information			

Yield: 20339 in²/lbTensile Strength @ Yield, ASTM D 882, MD: 4000 to 6500 psiTensile Strength @ Break, ASTM D 882, TD: 3800 to 5000 psiElongation @ Break, ASTM 882, MD: 200 to 300%Elongation @ Break, ASTM 882, TD: 400 to 500%Secant Modulus, ASTM D 882, MD: 83000 to 110000 psiSecant Modulus, ASTM D 882, TD: 90000 to 115000 psiGraves Tear (initial), ASTM D 1004, MD: 275 to 325 g/milGraves Tear (initial), ASTM D 1004, TD: 250 to 300 g/milDimensional Stability, ASTM D1204, TD, 300°F, 10 min: <2% shrinkageDimensional Stability, ASTM D1204, MD, 300°F, 10 min: <1.5% shrinkageCoef of Friction, ASTM D1894, Vs Metal - Dynamic: 0.4 to 0.7Coef of Friction, ASTM D1894, Vs Itself - Dynamic: 0.8 to 1.2

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT