

TECHNO AES 145HA

Acrylonitrile Ethylene Styrene

Techno Polymer America, Inc.

Message:

Weather-resistant resin for exterior automobile parts without painting
Satisfying the three requirements for exterior part resins: high impact strength under low temperature, high heat distortion temperature, and weather-resistance
Specific gravity that is 10% lower than that of PC/ASA resin to enable lower part weight
Designed for easy and consistent injection molding to enable greater design flexibility, faster cycle times, and reduced scrap, thus resulting in higher productivity
The best material for exterior automobile parts that require a higher aesthetic appearance

General Information			
Features	Fast Molding Cycle		
	Good Flexibility		
	Good Weather Resistance		
	High Impact Resistance		
	Low Temperature Impact Resistance		
	Medium Heat Resistance		
	Pleasing Surface Appearance		
Uses	Automotive Exterior Parts		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/10.0 kg)	53	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	46.0	MPa	ASTM D638
Flexural Modulus	2410	MPa	ASTM D790
Flexural Strength	64.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-30°C	69	J/m	
23°C	120	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	95.0	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	82.2 to 93.3	°C	
Drying Time	3.0 to 5.0	hr	

Rear Temperature	199 to 232	°C
Middle Temperature	199 to 232	°C
Front Temperature	199 to 232	°C
Mold Temperature	48.9 to 71.1	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

