

TECHNAMID® A A-SV30-A

Polyamide 66

Poly Plastic

Message:

TECHNAMID® A A-SV30-A is a Polyamide 66 (Nylon 66) product filled with glass fiber. It is available in Europe.

General Information		
Filler / Reinforcement	Glass Fiber	
Physical	Nominal Value	Unit
Density	1.35	g/cm³
Molding Shrinkage	0.30 to 0.80	%
Water Absorption		
Saturation, 23°C	5.0	%
Equilibrium, 23°C, 50% RH	1.9	%
Mechanical	Nominal Value	Unit
Tensile Stress (Yield)	165	MPa
Tensile Strain (Break)	4.0	%
Flexural Modulus (23°C)	9500	MPa
Flexural Stress	240	MPa
Impact	Nominal Value	Unit
Charpy Unnotched Impact Strength (20°C)	55	kJ/m²
Thermal	Nominal Value	Unit
Heat Deflection Temperature (1.8 MPa, Unannealed)	240	°C
Melting Temperature	260	°C
Electrical	Nominal Value	Unit
Surface Resistivity (2.00 mm)	1.0E+13	ohms
Volume Resistivity	1.0E+14	ohms·cm
Electric Strength (2.00 mm)	20	kV/mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT