

Polifil® PP GFPPCC-40

Polypropylene Homopolymer

The Plastics Group

Message:

Polifil® GFPPCC series compounds are homopolymer polypropylenes reinforced with chemically coupled glass fibers. These compounds offer superior strength and stiffness, improved elevated temperature performance, better creep resistance, higher impact strength, and higher resistance to high temperature water than conventional glass fiber reinforced polypropylenes. These compounds are used in chemical resistance applications, appliances, electrical components, automotive, irrigation and utility products. Standard processing techniques are applicable. Use this information as a guide to aid you in selecting the proper resin for your application. TPG will custom compound and fine-tune our formulations for your application.

General Information			
UL YellowCard	E84888-251659		
Filler / Reinforcement	Glass Fiber,40% Filler by Weight		
Features	Chemically Coupled		
	Good Chemical Resistance		
	Good Creep Resistance		
	Good Stiffness		
	High Impact Resistance		
	High Strength		
	Homopolymer		
Uses	Appliances		
	Automotive Applications		
	Electrical Parts		
	Irrigation Applications		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.22	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	4.0 to 10	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.18 mm)	0.30	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	102		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	4830	MPa	ASTM D638
Tensile Strength (23°C)	110	MPa	ASTM D638
Tensile Elongation			ASTM D638
Yield, 23°C	2.0	%	
Break, 23°C	3.0	%	
Flexural Modulus - Tangent (23°C)	6760	MPa	ASTM D790

Flexural Strength (23°C)	145	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	110	J/m	ASTM D256
Gardner Impact (23°C, 12.7 mm)	0.452	J	ASTM D3029
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	157	°C	
1.8 MPa, Unannealed	149	°C	
Injection	Nominal Value	Unit	
Drying Temperature	82.2 to 104	°C	
Drying Time	1.0 to 2.0	hr	
Rear Temperature	210 to 221	°C	
Middle Temperature	216 to 227	°C	
Front Temperature	227 to 238	°C	
Nozzle Temperature	227 to 249	°C	
Processing (Melt) Temp	232 to 260	°C	
Mold Temperature	48.9 to 65.6	°C	
Injection Rate	Fast		
Back Pressure	0.172 to 0.517	MPa	
Screw Speed	30 to 60	rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

