

Versaflex™ CL E85

Thermoplastic Elastomer

PolyOne Corporation

Message:

Versaflex™CL E85 is a material with extremely high transparency, high performance and high temperature heating. It is an ideal material for medical and food packaging. Versaflex™CL E85 also did not use plasticizers.
New Products. Commercial norms have not yet been established.

- Flexible
- Special formula without plasticizer
- High transparency

General Information			
Features	Good flexibility		
	Definition, high		
Uses	Films		
	Personal care		
	Bottle		
	Medical/nursing supplies		
Agency Ratings	FDA 21 CFR 177.1210 2		
	ISO 10993 Part 4		
	ISO 10993 Part 5		
	USP Class VI		
RoHS Compliance	RoHS compliance		
Appearance	Clear/transparent		
Forms	Particle		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.878	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 10 sec)	85		ASTM D2240
Films	Nominal Value	Unit	Test Method
Oxygen Permeability (21°C, 1800 μm)	380	cm ³ ·mm/m ² /atm/24 hr	ASTM D3985
Oxygen Transmission Rate (21°C, 1800 μm)	3200	cm ³ /m ² /24 hr	ASTM D3985
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ¹			ASTM D412
100% strain, 23°C ²	5.18	MPa	ASTM D412
300% strain, 23°C ³	8.00	MPa	ASTM D412
Tensile Strength (Break, 23°C)	10.7	MPa	ASTM D412
Tensile Elongation (Break, 23°C)	450	%	ASTM D412

Compression Set			ASTM D395B
22°C, 22 hr	20	%	ASTM D395B
45°C, 22 hr	51	%	ASTM D395B
70°C, 22 hr	67	%	ASTM D395B
100°C, 22 hr	72	%	ASTM D395B
Fill Analysis	Nominal Value	Unit	Test Method
Apparent Viscosity			ASTM D3835
200°C, 1340 sec ⁻¹	180	Pa·s	ASTM D3835
200°C, 11200 sec ⁻¹	37.0	Pa·s	ASTM D3835
Extrusion	Nominal Value	Unit	
Melt Temperature	182 - 204	°C	
Die Temperature	171 - 199	°C	
Extrusion instructions			
<p>Color concentrates with polypropylene (PP), ethylene vinyl acetate (EVA), or low density polyethylene (PE) carriers are most suitable for coloring Versaflex™ CL E85. Improved color dispersion can be achieved by using higher melt flow concentrates (with a melt flow from 25 - 40g/10 min). Typical loadings for color concentrates are 1% to 5% by weight. Liquid color can be used, but mineral oil based carriers may have a significant effect on the final hardness value. Concentrates based on PVC should not be used. A high color match consistency can be obtained by using precolored compounds available from GLS. The final determination of color concentrate suitability should be determined by customer trials. Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polyethylene (PE) or polypropylene (PP). Drying is not Required. Rear Zone = 330-370F Center Zone = 350-400F Front Zone = 360-420F Screw Speed = 100-500 RPM</p>			
NOTE			
1.	2 hours		
2.	Mouth die c		
3.	C mould		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

