

Razamid® B126 GR35

Polyamide 6

Razin™ Engineering Plastics

Message:

Razamid B126 GR35 is an injection grade heat stabilized black color polyamide 6 resin reinforced with 35% Glass Fiber. It combines good strength, stiffness and toughness as well as excellent heat, chemical and abrasion resistance, design for air take manifold.

General Information			
Filler / Reinforcement	Glass Fiber,35% Filler by Weight		
Features	Good Abrasion Resistance		
	Good Chemical Resistance		
	Good Stiffness		
	Good Strength		
	Good Toughness		
	High Heat Resistance		
Appearance	Black		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.42	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.40	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	195	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	11000	MPa	ASTM D790
Flexural Strength	285	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Area) (23°C)	20.0	kJ/m ²	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	220	°C	
1.8 MPa, Unannealed	212	°C	
Vicat Softening Temperature	210	°C	ASTM D1525
Peak Melting Temperature	225	°C	ASTM D3418
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+12	ohms	IEC 60093
Volume Resistivity	1.0E+13	ohms · cm	IEC 60093
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 100	°C	
Drying Time	2.0 to 4.0	hr	

Rear Temperature	220 to 240	°C
Middle Temperature	240 to 260	°C
Front Temperature	255 to 275	°C
Processing (Melt) Temp	270 to 290	°C
Mold Temperature	80.0 to 90.0	°C
Injection Pressure	55.0 to 140	MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

