

DESLON™ 6 DSC114GM

Polyamide 6

DESCO Co., Ltd.

Message:

Descriptions: DESLON™ DSC114GM is one of the brands which made by Polyamide6 that filled Glass Fiber & Mineral Filler 20%. It provides good mechanical property and good heat resistance.

Applications: DESLON™ DSC114GM is one of the most-used for surface appearance, good mechanical property and excellent heat resistance goods due to excellent fluidity, such as Engine cover, etc.

General Information			
Filler / Reinforcement	Glass \mineral, 20% filler by weight		
Features	Good liquidity		
	Heat resistance, high		
	Excellent appearance		
Uses	Handle		
	Electrical/Electronic Applications		
	Industrial application		
	Application in Automobile Field		
	Shell		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.28	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.60 - 0.70	%	
Water Absorption (23°C, 24 hr)	1.4	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	88.3	MPa	ASTM D638
Tensile Elongation (Break)	4.0	%	ASTM D638
Flexural Modulus	5100	MPa	ASTM D790
Flexural Strength	147	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	49	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	210	°C	ASTM D648
1.8 MPa, not annealed	140	°C	ASTM D648
Melting Temperature	220	°C	DSC
Flammability	Nominal Value		Test Method

Flame Rating	HB	UL 94
Injection	Nominal Value	Unit
Drying Temperature	80.0 - 120	°C
Drying Time	3.0 - 5.0	hr
Suggested Max Moisture	< 0.20	%
Rear Temperature	240 - 250	°C
Middle Temperature	250 - 260	°C
Front Temperature	250 - 270	°C
Nozzle Temperature	255 - 270	°C
Processing (Melt) Temp	255 - 270	°C
Mold Temperature	80.0 - 100	°C
Injection instructions		

Speed: 30 to 60%Pressure 1st: 30 to 70%Pressure 2nd: 30 to 70Holding Pressure: 10 to 30%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

