

ICORENE® 3590

Linear Low Density Polyethylene
ICO Polymers EMEA, A Division of A. Schulman

Message:

ICORENE® 3590 is a linear low density polyethylene specifically developed for rotational moulding.
ICORENE® 3590 is a very fast processing material suitable for use in many different applications. It has a good balance of properties such as toughness, easy flow and stiffness.

General Information			
Additive	UV Stabilizer		
Features	General Purpose		
	Good Flow		
	Good Moldability		
	Good Processability		
	Good Stiffness		
	Good Toughness		
	Good UV Resistance		
Uses	General Purpose		
Appearance	Natural Color		
	Unspecified Color		
Forms	Powder		
Processing Method	Rotational Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.935	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	9.0	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	56		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	17.0	MPa	ASTM D638
Flexural Modulus	550	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Drop Impact Resistance ¹ (-20°C)	160	J/cm	Internal Method
NOTE			

1. Based on ISO 6603

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

