

ADENE® O07MJBGD00

Polypropylene Copolymer

A.D. Compound S.p.A.

Message:

PP Stabilized Copolymer Industrial Black 30% Talc filled

General Information			
Filler / Reinforcement	Talc filler, 30% filler by weight		
Recycled Content	Yes		
Features	Copolymer		
Appearance	Black		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	11	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	2100 - 2500	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	6.0 - 10	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	54.5	°C	ISO 306
Heat Deflection Temperature	60	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

