

# ResinDirect HDPE03

High Density Polyethylene

ResinDirect

Message:

Hexene Copolymer.

General Information			
Features	Copolymer		
Forms	Pellets		
Processing Method	Blow Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.955	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.35	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup> (Yield)	27.6	MPa	ASTM D638
Tensile Elongation <sup>2</sup> (Break)	600	%	ASTM D638
Flexural Modulus <sup>3</sup>	1380	MPa	ASTM D790
NOTE			
1.	5.1 mm/min		
2.	5.1 mm/min		
3.	2.5 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT