

Fiberfil® J-61/10

Polypropylene Copolymer
Fiberfil® Engineered Plastics Inc.

Message:
Fiberfil® J-61/10 is a polypropylene copolymer (PP Copoly) material, and the filler is 10% glass fiber reinforced material. This product is available in North America. Fiberfil® The main characteristics of J-61/10 are: copolymer.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 10% filler by weight		
Features	Copolymer		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.978	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	13	g/10 min	ASTM D1238
Molding Shrinkage - Flow			ASTM D955
3.18 mm	0.40	%	ASTM D955
6.35 mm	0.50	%	ASTM D955
Water Absorption (24 hr)	0.010	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	105		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2070	MPa	ASTM D638
Tensile Strength (23°C)	34.5	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	5.0	%	ASTM D638
Flexural Modulus - Tangent (23°C)	1930	MPa	ASTM D790
Flexural Strength (23°C)	51.7	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	64	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	152	°C	ASTM D648
1.8 MPa, not annealed	135	°C	ASTM D648
Additional Information			

Rockwell Hardness, ASTM D785, R-Scale: 100 to 110

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

