

# Hostacom TRC 411N D71500

Polypropylene  
LyondellBasell Industries

**Message:**

Hostacom TRC 411N is a 15% talc filled elastomer modified PP, with high flowability, good impact/stiffness balance, outstanding scratch resistance, low odour and low emissions. This grade is delivered in customer customized colors, this Data Sheet is giving general properties, some of them may be slightly altered upon color selected.

For regulatory compliance information, see Hostacom TRC 411N D71500 Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS).

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

General Information			
Filler / Reinforcement	Talc filler, 15% filler by weight		
Features	Low VOC		
	Low volatilization		
	Low density		
	Rigid, good		
	Impact resistance, high		
	Impact resistance, good		
	Good UV resistance		
	Workability, good		
	Good color stability		
	Good wear resistance		
	High liquidity		
	Low temperature impact resistance		
	Scratch resistance		
	The smell is low to none		
	Good appearance		
Uses	ductility		
	Excellent appearance		
Appearance	Application in Automobile Field		
	Car interior parts		
	Car dashboard		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.02	g/cm³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	19	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus <sup>1</sup> (23°C)	1800	MPa	ISO 178/A


Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	30	kJ/m <sup>2</sup>	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	90.0	°C	ISO 75-2/B
NOTE			
1.	1.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
 Phone: +86 13424755533  
 Email: sales@su-jiao.com  
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT