

Durethan® BKV 30 H2.0 EF DUS029 901510

Polyamide 6

LANXESS Corporation

Message:

PA 6, 30 % glass fibers, injection molding, improved flowability, heat-aging stabilized

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Additive	heat stabilizer		
Features	Good liquidity		
	Thermal Stability		
Agency Ratings	EC 1907/2006 (REACH)		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.40	g/cm ³	ISO 1183
Apparent Density	0.60	g/cm ³	ISO 60
Molding Shrinkage			ISO 2577
Vertical flow direction: 280°C, 2.00mm ¹	0.70	%	ISO 2577
Vertical flow direction: 120°C, 4 hours, 2.00mm ²	0.14	%	ISO 2577
Flow direction: 280°C, 2.00mm ³	0.23	%	ISO 2577
Flow direction: 120°C, 4 hours, 2.00mm ⁴	0.050	%	ISO 2577
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	9500	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	155	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	2.9	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	50	kJ/m ²	ISO 179/1eU
23°C	65	kJ/m ²	ISO 179/1eU
Notched Izod Impact			ISO 180/1A
-30°C	< 10	kJ/m ²	ISO 180/1A
23°C	10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength			ISO 180/1U
-30°C	50	kJ/m ²	ISO 180/1U
23°C	60	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	220	°C	ISO 75-2/B

1.8 MPa, not annealed	205	°C	ISO 75-2/A
Linear thermal expansion coefficient			ISO 11359-2
Flow: 23 to 55°C	2.0E-5	cm/cm/°C	ISO 11359-2
Lateral: 23 to 55°C	9.0E-5	cm/cm/°C	ISO 11359-2
Additional Information	Nominal Value	Test Method	
ISO Shortname	PA 6,MHR,12-090,GF30	ISO 1874	
Residual Moisture Content	0.030 - 0.12	%	Karl Fisher
Injection	Nominal Value	Unit	Test Method
Drying Temperature - Dry Air Dryer	80.0	°C	
Drying Time - Dry Air Dryer	2.0 - 6.0	hr	
Processing (Melt) Temp	270 - 290	°C	
Mold Temperature	80.0 - 120	°C	
NOTE			
1.	60x60x2mm, 80°C MT, 600 bar		
2.	60x60x2mm		
3.	60x60x2mm, 80°C MT, 600 bar		
4.	60x60x2mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT