

# Reon 67-01

Polyvinyl Chloride Homopolymer

Reliance Industries Limited

## Message:

Reon 67-01 is a medium molecular weight suspension type PVC resin suitable for rigid extrusion products. It is specially recommended for rigid pipes & conduits, rigid profiles, rigid sheets, unplasticised tubular film etc. Its combination of medium molecular weight with high apparent bulk density makes it suitable for easy processing at high output rate, still maintaining the high mechanical properties. Its balanced heat loss property does not allow static to develop and reduces the flow time. At the same time the resin contains minimum volatiles. The narrow range of porosity of Reon 67-01 makes it easy to maintain a uniform fusion point at constant lubricant level. Uniform coarseness of the grains of this resin results in easy bulk handling, minimum requirement of lubricant and more uniform fluxing in the extruder.

General Information	
Features	Good Processability Homopolymer Medium Molecular Weight
Uses	Conduit Film Piping Profiles Sheet
Agency Ratings	IS 10151
Appearance	Clear/Transparent
Processing Method	Blown Film Calendering Extrusion

Physical	Nominal Value	Unit	Test Method
Apparent Density	0.55	g/cm <sup>3</sup>	ASTM D1895
K-Value <sup>1</sup>	67.0		
Inherent Viscosity	0.92		ASTM D1243
Particle Size Distribution			ASTM D1921
Retention on ASTM 40 mesh	< 0.10	%	
Retention on ASTM 60 mesh	< 5.0	%	
Through ASTM 140 mesh	< 25	%	
Heat Loss	< 0.30	%	ASTM D3030
Dark Resin - for 100 g resin	< 10.0	count/g	
Flow Time	< 25.0	sec	ASTM D1895
Porosity - DOP	0.210 to 0.290	cm <sup>3</sup> /g	ASTM D3367
Residual Vinyl Chloride Monomer	< 2	ppm	ASTM D3749

NOTE

1.

@ 1% in cyclohexanone

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

