Novamid® 1010J

Polyamide 6

DSM Engineering Plastics

Message:

Novamid[®] 1010J is a Polyamide 6 (Nylon 6) material. It is available in Asia Pacific for injection molding. Primary attribute of Novamid[®] 1010J: Low Viscosity.

| General Information | | | |
|---|-------------------|-------|-------------|
| Features | Low Viscosity | | |
| Processing Method | Injection Molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 1.13 | g/cm³ | ISO 1183 |
| Water Absorption (Equilibrium, 23°C, 50% RH) | 2.8 | % | ISO 62 |
| Viscosity Number | 118 | cm³/g | ISO 307 |
| Thermal | Nominal Value | Unit | Test Method |
| Melting Temperature ¹ | 220 | °C | ISO 11357-3 |
| Injection | Nominal Value | Unit | |
| Drying Temperature | 80.0 | °C | |
| Drying Time | 4.0 to 8.0 | hr | |
| Rear Temperature | 230 to 235 | °C | |
| Middle Temperature | 235 to 250 | °C | |
| Front Temperature | 240 to 260 | °C | |
| Nozzle Temperature | 240 to 270 | °C | |
| Processing (Melt) Temp | 240 to 275 | °C | |
| Mold Temperature | 50.0 to 80.0 | °C | |
| Injection Rate | Moderate-Fast | | |
| Back Pressure | 3.00 to 10.0 | MPa | |
| Screw Compression Ratio | 2.5:1.0 | | |
| NOTE | | | |
| 1. | 10°C/min | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533 Email: sales@su-jiao.com No. 215, Lianhe North Road, Fengxian District, Shanghai, China

