

KEBABLEND® / M 13/26 PA12

Polyamide 12

BARLOG plastics GmbH

Message:

PA12 functional compound, polymer bonded magnet

General Information			
Resin ID (ISO 1043)	PA 12 mod.		
Physical	Nominal Value	Unit	Test Method
Density	3.40	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	10000	MPa	ISO 527-2
Tensile Stress (Break)	60.0	MPa	ISO 527-2
Tensile Strain (Break)	1.9	%	ISO 527-2
Thermal	Nominal Value	Unit	Test Method
Melting Temperature ¹	178	°C	ISO 11357-3
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

