

Dryflex® A2 500350

Styrene Ethylene Butylene Styrene Block Copolymer

ELASTO

Message:

Dryflex A2 500350: Thermoplastic Elastomer

Material Type: TPS-SEBS

Hardness: 35 Shore A (4mm)

Service Temperature Range: -50 -- +125°C (unstressed material)

Colour: Opaque/White, but the base material can be available in any colour.

Presentation: Free flowing pellets that can be processed without predrying, when stored under normal conditions.

Weather Resistance: Good

Chemical Resistance: Good (excluding organic solvents, aromatic- and vegetable oils)

Recyclability: 100% recyclable

Special Features

The material Shows good adhesion onto PC/ABS, PC and ABS

General Information			
Features	Recyclable materials		
	Workability, good		
	Good adhesion		
	Good chemical resistance		
	Good weather resistance		
Appearance	White		
	Opacity		
	Available colors		
Forms	Particle		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.940	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	25	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 4.00 mm)	35		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			ASTM D638
100% secant	1.00	MPa	ASTM D638
300% secant	2.00	MPa	ASTM D638
Tensile Strength	3.00	MPa	ASTM D638
Tensile Elongation (Break)	550	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method

Tear Strength	16.0	kN/m	ASTM D624
Thermal	Nominal Value	Unit	
Service Temperature - Unstressed Material	-50 - 125	°C	
Injection	Nominal Value	Unit	
Rear Temperature	210 - 250	°C	
Middle Temperature	210 - 250	°C	
Front Temperature	210 - 250	°C	
Mold Temperature	30 - 60	°C	
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	210 - 250	°C	
Cylinder Zone 2 Temp.	210 - 250	°C	
Cylinder Zone 3 Temp.	210 - 250	°C	
Cylinder Zone 4 Temp.	210 - 250	°C	
Cylinder Zone 5 Temp.	210 - 250	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

