

Chemlon® 133 GVH

Polyamide 66

Teknor Apex Company (Chem Polymer)

Message:

Chemlon® 133 GVH is a Polyamide 66 (Nylon 66) material filled with 33% glass fiber. It is available in Asia Pacific, Europe, or North America for injection molding. Primary attribute of Chemlon® 133 GVH: Flame Rated.

General Information			
UL YellowCard	E90654-100046570	E90654-252577	
Filler / Reinforcement	Glass Fiber,33% Filler by Weight		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.59	g/cm³	ASTM D792
Molding Shrinkage - Flow	0.15 to 0.30	%	ASTM D955
Water Absorption (24 hr)	0.60	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	134	MPa	ASTM D638
Tensile Elongation			ASTM D638
Yield	2.0	%	
Break	2.0	%	
Flexural Modulus	8960	MPa	ASTM D790
Flexural Strength	193	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	110	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	243	°C	ASTM D648
Melting Temperature	257	°C	DSC
CLTE - Flow	5.1E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+18	ohms·cm	ASTM D257
Dielectric Strength (3.00 mm)	15	kV/mm	ASTM D149
Comparative Tracking Index (CTI)	300	V	UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.800 mm)	V-0		UL 94
Oxygen Index	33	%	ASTM D2863
FMVSS Flammability	PASSES		FMVSS 302
Injection	Nominal Value	Unit	
Drying Temperature	79.4	°C	
Suggested Max Moisture	0.20	%	

Suggested Max Regrind	25	%
Rear Temperature	241 to 257	°C
Middle Temperature	263 to 279	°C
Front Temperature	263 to 285	°C
Nozzle Temperature	263 to 285	°C
Processing (Melt) Temp	263 to 285	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

