

Bayflex® MP-25000

Polyurethane (Polyether, MDI)

Covestro - PUR

Message:

Bayflex MP-25,000 is a solid elastomer which has a flexural modulus of 25,000 psi (172 MPa) at room temperature.* It is processed on reaction injection molding (RIM) equipment and is used for rollers, gaskets, and encapsulated windows. This system combines rapid demold times, excellent integrity at demold, improved release characteristics and outstanding physical properties. As with any product, use of the Bayflex MP-25,000 system in a given application must be tested (including field testing, etc.) in advance by the user to determine suitability.

Bayflex MP-25,000 is a formulated RIM system supplied as two liquid components. Component A is a diphenylmethane diisocyanate (MDI) prepolymer, and Component B is a polyether polyol. Note: Component B should be agitated thoroughly prior to transfer of contents from the drum to the day tank.

General Information			
Features	Good demoulding performance		
Uses	Washer		
	Roller		
	Doors and Windows		
Forms	Liquid		
Processing Method	Reaction Injection Molding (RIM)		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm ³	ASTM D792, ASTM D1622
Molding Shrinkage - Flow (3.00 mm)	1.5	%	Internal method
Water Absorption (24 hr, 3.00 mm)	3.3	%	Internal method
Water absorption rate-240 hr (3.00 mm)	5.0	%	Internal method
Low Temperature Brittleness (-50°C, 3.00 mm)	No Cracking		ASTM D746
Water Immersion, Length Increase (3.00 mm)	1.4	%	Internal method
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (shaw d, 3.00mm)	50		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break, 3.00 mm)	24.1	MPa	ASTM D638
Flexural Modulus			ASTM D790
-30°C, 3.00 mm	441	MPa	ASTM D790
23°C, 3.00 mm	172	MPa	ASTM D790
65°C, 3.00 mm	124	MPa	ASTM D790
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
20% strain ¹	7.93	MPa	ASTM D412
50% strain, 3.00mm ²	8.27	MPa	ASTM D412
100% strain, 3.00mm ³	9.65	MPa	ASTM D412
Tensile Strength (Break, 3.00 mm)	24.1	MPa	ASTM D412

Tensile Elongation (Break, 3.00 mm)	250	%	ASTM D412
Tear Strength ⁴ (3.00 mm)	85.8	kN/m	ASTM D624
Thermal	Nominal Value	Unit	Test Method
CLTE - Flow (3.00 mm)	1.4E-4	cm/cm/°C	ASTM D696
Thermoset	Nominal Value	Unit	Test Method
Thermoset Components ⁵			
Component a	Mixing ratio by weight: 48		
Component B	Mixing ratio by weight: 100		
Shelf Life (30°C)	26	wk	
Demold Time	0.50	min	
Additional Information	Nominal Value	Unit	Test Method

Part A
Type: Isocyanate
Specific Gravity @ 25°C: 1.21
Viscosity @25°C: 700 mPa-s
Flash Point PMCC: 213 °C
Part B
Type: Polyol
Specific Gravity @ 25°C: 1.03
Viscosity @25°C: 1200 mPa-s
Flash Point PMCC: 193 °C
Molding Parameters
Material Temperature: 32 to 42 °C
Mold Temperature: 65 to 75 °C

NOTE	
1.	Die C, 510 mm/min
2.	C mold, 510mm/min
3.	Mouth die C, 510mm/min
4.	C mould
5.	105 Index

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

