

NYLOY® MG-0023N-V0

Polyamide 66
Nytex Composites Co., Ltd.

Message:

NYLOY® MG-0023N-V0 is a Polyamide 66 (Nylon 66) material filled with 23% glass fiber. It is available in Asia Pacific or North America for injection molding.
Important attributes of NYLOY® MG-0023N-V0 are:
Flame Rated
Flame Retardant

General Information			
Filler / Reinforcement	Glass Fiber,23% Filler by Weight		
Additive	Flame Retardant		
Features	Flame Retardant		
Appearance	Natural Color		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.31	g/cm³	ASTM D792
Molding Shrinkage			ASTM D955
Flow	0.48	%	
Across Flow	1.4	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	117		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	145	MPa	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Flexural Modulus	8430	MPa	ASTM D790
Flexural Strength	206	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	93	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	235	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating (3.18 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Processing (Melt) Temp	270 to 300	°C	
Mold Temperature	80.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

