

ADDILENE PMD 50271

Polypropylene
ADDIPLAST

Message:

ADDILENE PMD 50271 is a Polypropylene material. It is available in Africa & Middle East, Asia Pacific, Europe, or Latin America.
Important attributes of ADDILENE PMD 50271 are:
Flame Rated
Flame Retardant
Rigid
Typical applications include:
Housings
Industrial Applications

General Information			
Additive	Flame Retardant		
Features	Flame Retardant		
	High Rigidity		
Uses	Electrical Housing		
	Industrial Applications		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.38	g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	16	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	80		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	70.0	MPa	ISO 527-2
Tensile Strain (Break)	4.0	%	ISO 527-2
Flexural Modulus	7000	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	5.5	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	18	kJ/m ²	ISO 179/1eU
Notched Izod Impact Strength	5.0	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	146	°C	ISO 75-2/Af
Vicat Softening Temperature	163	°C	ISO 306/A50
Melting Temperature (DSC)	165	°C	ISO 3146
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13	ohms	IEC 60093

Volume Resistivity	1.0E+14	ohms·cm	IEC 60093
Comparative Tracking Index (Solution A)	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	V-2		UL 94
Glow Wire Ignition Temperature	750	°C	IEC 60695-2-13
Oxygen Index	23	%	ISO 4589-2

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

