

POCAN® DP 7318 000000

Polybutylene Terephthalate

LANXESS GmbH

Message:

PBT, 17 % white pigments, injection moulding, improved light reflection, low tendency to warp

General Information			
Features	Low warpage		
Agency Ratings	EC 1907/2006 (REACH)		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.50	g/cm ³	ISO 1183
Apparent Density	0.90	g/cm ³	ISO 60
Melt Volume-Flow Rate (MVR) (260°C/2.16 kg)	27.0	cm ³ /10min	ISO 1133
Molding Shrinkage			
Vertical flow direction: 260°C, 3.00mm ¹	1.9	%	ISO 2577
Vertical flow direction: 110°C, 48 hours, 3.00mm ²	0.20	%	ISO 294-4
Flow direction: 260°C, 3.00mm ³	1.9	%	ISO 2577
Flow direction: 110°C, 48 hours, 3.00mm ⁴	0.20	%	ISO 2577
Water Absorption			
Saturated, 23°C	0.40	%	ISO 62
Equilibrium, 23°C, 50% RH	0.20	%	ISO 62
Viscosity Number (Reduced Viscosity)	94.0	ml/g	ISO 1628
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	3400	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	57.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	10	%	ISO 527-2/5
Flexural Modulus ⁵ (23°C)	3200	MPa	ISO 178/A
Flexural Stress ⁶ (23°C)	95.0	MPa	ISO 178
Flexural Strain at Flexural Strength ⁷ (23°C)	6.0	%	
ISO Shortname	PBT, GHMR, 09-030, MD17		ISO 7792
Residual Moisture Content	0.0 - 0.020	%	Karl Fisher
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength (23°C)	130	kJ/m ²	ISO 179/1eU
Notched Izod Impact (23°C)	< 10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength (23°C)	110	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method

Heat Deflection Temperature (0.45 MPa, Unannealed)	160	°C	ISO 75-2/B
Vicat Softening Temperature	190	°C	ISO 306/B50
Melting Temperature ⁸	225	°C	ISO 11357-3
Linear thermal expansion coefficient			ISO 11359-2
Flow: 23 to 55°C	9.0E-5	cm/cm/°C	ISO 11359-2
Lateral: 23 to 55°C	9.0E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index (Solution A)	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.800 mm	HB		UL 94
1.60 mm	HB		UL 94
Injection	Nominal Value	Unit	Test Method
Drying Temperature - Circulation Dryer	120	°C	
Drying Time - Circulation Dryer	4.0 - 8.0	hr	
Processing (Melt) Temp	250 - 270	°C	
Mold Temperature	80.0 - 100	°C	
NOTE			
1.	150x150x3; MT 80°C; 600 Bar		
2.	150x150x3		
3.	150x150x3; MT 80°C; 600 Bar		
4.	150x150x3		
5.	2.0 mm/min		
6.	2.0 mm/min		
7.	Pull Rate: 2 mm/min; 50% RH		
8.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

