

KOCETAL® TC701

Acetal (POM) Copolymer

Kolon Plastics, Inc.

Message:

Kocetal TC701 is Mineral reinforced grade for good dimensional stability.

General Information			
Filler / Reinforcement	Mineral		
Features	Good Dimensional Stability		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.44	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	24	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.8	%	ASTM D955
Water Absorption (Equilibrium, 23°C, 60%RH)	0.20	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	81		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	65.0	MPa	ASTM D638
Tensile Elongation (Yield, 23°C)	25	%	ASTM D638
Flexural Modulus (23°C)	3100	MPa	ASTM D790
Flexural Strength (23°C)	100	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	45	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	160	°C	
1.8 MPa, Unannealed	120	°C	
Melting Temperature	166	°C	
CLTE - Flow	1.0E-4	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	ASTM D257
Volume Resistivity	1.0E+14	ohms · cm	ASTM D257
Dielectric Strength	19	kV/mm	ASTM D149
Dielectric Constant	3.70		ASTM D150
Dissipation Factor (1 MHz)	6.0E-3		ASTM D150
Flammability	Nominal Value	Unit	Test Method

Flame Rating	HB	UL 94
Injection	Nominal Value	Unit
Drying Temperature	80.0	°C
Drying Time	3.0	hr
Suggested Max Regrind	30	%
Rear Temperature	170 to 190	°C
Middle Temperature	190 to 210	°C
Front Temperature	200 to 220	°C
Nozzle Temperature	200 to 220	°C
Processing (Melt) Temp	165 to 220	°C
Mold Temperature	70.0 to 120	°C
Injection Pressure	68.6 to 118	MPa
Holding Pressure	98.1	MPa
Back Pressure	1.96 to 4.90	MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

