

# KMI PBS KM803

Polybutylene Succinate

KMI Group Inc.

## Message:

KMI PBS KM803 is a Polybutylene Succinate (PBS) product. It can be processed by injection molding and is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Applications of KMI PBS KM803 include business/office goods, consumer goods and kitchenware. Primary characteristic: eco-friendly/green.

General Information			
Features	Biodegradable		
Uses	Disposable Tableware		
	Toys		
	Writing Instruments		
Appearance	White		
	Yellow		
Forms	Granules		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.20 to 1.28	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR)	< 25	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	30.0 to 40.0	MPa	ISO 527-2
Tensile Strain (Break)	> 300	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	> 5.0	kJ/m <sup>2</sup>	ISO 179
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	> 90.0	°C	ISO 868
Melting Temperature (DSC)	110 to 116	°C	DSC

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT