

POCAN® S 7020 000000

Polybutylene Terephthalate

LANXESS GmbH

Message:

PBT, non-reinforced, injection molding, extrusion, flame retardant, improved impact strength

General Information			
UL YellowCard	E245249-474059		
Additive	Flame Retardant		
Features	Flame Retardant		
	Good Impact Resistance		
Processing Method	Extrusion		
	Injection Molding		
Multi-Point Data	Viscosity vs. Shear Rate (ISO 11403-2)		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.38	g/cm ³	ISO 1183
Apparent Density	0.80	g/cm ³	ISO 60
Melt Volume-Flow Rate (MVR) (270°C/5.0 kg)	50.0	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 2577
Across Flow : 250°C, 2.00 mm ¹	1.8	%	
Across Flow : 120°C, 4 hr, 2.00 mm ²	0.40	%	
Flow : 250°C, 2.00 mm ³	1.8	%	
Flow : 120°C, 4 hr, 2.00 mm ⁴	0.40	%	
Water Absorption			ISO 62
Saturation, 23°C	0.60	%	
Equilibrium, 23°C, 50% RH	0.20	%	
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	120	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2300	MPa	ISO 527-2/1
Tensile Stress (Yield, 23°C)	45.0	MPa	ISO 527-2/50
Tensile Strain (Yield, 23°C)	4.5	%	ISO 527-2/50
Nominal Tensile Strain at Break (23°C)	> 15	%	ISO 527-2/50
Tensile Creep Modulus			ISO 899-1
1 hr	2300	MPa	
1000 hr	1600	MPa	
Flexural Modulus ⁵ (23°C)	2300	MPa	ISO 178/A

Flexural Stress			ISO 178/A
3.5% Strain, 23°C	70.0	MPa	
23°C ⁶	75.0	MPa	
Flexural Strain at Flexural Strength (23°C) ⁷	5.3	%	ISO 178/A
Halving Interval			IEC 60216
Electric Strength	5.8	°C	
Tensile Impact Strength	5.3	°C	
Tensile Strength	5.8	°C	
Temperature Index			IEC 60216
Electric Strength, 20000 hr	135	°C	
Tensile Impact Strength, 20000 hr	120	°C	
Tensile Strength, 20000 hr	135	°C	
Electrolytical Corrosion (23°C)	A 1		IEC 60426
ISO Shortname	PBT, GFHMPPR, 11-020; ISO 1043-PBT FR (17)		ISO 7792
Residual Moisture Content	0.0 to 0.020	%	Karl Fisher
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	< 10	kJ/m ²	
23°C	< 10	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	110	kJ/m ²	
23°C	No Break		
Notched Izod Impact Strength			ISO 180/1A
-40°C	< 10	kJ/m ²	
-30°C	< 10	kJ/m ²	
23°C	< 10	kJ/m ²	
Unnotched Izod Impact Strength			ISO 180/1U
-30°C	65	kJ/m ²	
23°C	No Break		
Multi-Axial Instrumented Impact Energy (23°C, Energy to Peak Force)	80.0	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	125	°C	ISO 75-2/B
1.8 MPa, Unannealed	65.0	°C	ISO 75-2/A
Vicat Softening Temperature	150	°C	ISO 306/B120
Ball Pressure Test (190°C)	Pass		IEC 60695-10-2
Melting Temperature ⁸	225	°C	ISO 11357-3
CLTE			ISO 11359-2
Flow : 23 to 55°C	1.1E-4	cm/cm/°C	
Transverse : 23 to 55°C	1.1E-4	cm/cm/°C	
Thermal Conductivity (23°C)	0.25	W/m/K	ISO 8302

RTI Elec	125	°C	UL 746
RTI Imp	115	°C	UL 746
RTI Str	125	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity (23°C)	> 1.0E+17	ohms·cm	IEC 60093
Electric Strength (23°C, 1.00 mm)	23	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
23°C, 100 Hz	3.80		
23°C, 1 MHz	3.60		
Dissipation Factor			IEC 60250
23°C, 100 Hz	4.0E-3		
23°C, 1 MHz	0.024		
Comparative Tracking Index (Solution A)	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.800 mm	V-2		
1.50 mm	V-0		
Glow Wire Flammability Index (0.800 mm)	960	°C	IEC 60695-2-12
Oxygen Index ⁹	30	%	ISO 4589-2
Injection	Nominal Value	Unit	Test Method
Drying Temperature - Circulation Dryer	120	°C	
Drying Time - Circulation Dryer	4.0 to 8.0	hr	
Processing (Melt) Temp	240 to 260	°C	
Mold Temperature	80.0 to 100	°C	
NOTE			
1.	60x60x2mm, 80°C MT, 600 bar		
2.	60x60x2mm		
3.	60x60x2mm, 80°C MT, 600 bar		
4.	60x60x2mm		
5.	2.0 mm/min		
6.	2.0 mm/min		
7.	2 mm/min		
8.	10°C/min		
9.	Procedure A		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

