

# Hanwha Total PP BJ192

Polypropylene

HANWHA TOTAL PETROCHEMICALS Co., Ltd.

## Message:

BJ192 is a polypropylene compound offering balanced rigidity and impact strength, and long-term heat-resistance. In particular, BI492 and BI792 display outstanding flexural modulus, surface hardness and thermal deformation temperatures, due to production using high crystalline PP.

General Information			
Features	Crystalline Good Chemical Resistance Good Impact Resistance Good Weather Resistance High Heat Resistance Medium Rigidity		
Uses	Automotive Exterior Parts Automotive Interior Parts Housings Tanks		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	0.910	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	1.5	g/10 min	ASTM D1238
Molding Shrinkage - Flow (2.00 mm)	1.4 to 1.8	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	80		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	25.5	MPa	ASTM D638
Tensile Elongation (Break)	500	%	ASTM D638
Flexural Modulus	1180	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	No Break		ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	100	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

