

Grivory® GVL-6H black 9839

Polyamide 66 + PA 6I/X

EMS-GRIVORY

Message:

Grivory® GVL-6H black 9839 is a Polyamide 66 + PA 6I/X (Nylon 66+Nylon 6I/X) material filled with 60% long glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America for injection molding.

Important attributes of Grivory® GVL-6H black 9839 are:

- Flame Rated
- Good Mold Release
- Heat Resistant
- Typical applications include:
 - Automotive
 - Electrical/Electronic Applications
 - Appliances
 - Engineering/Industrial Parts
 - Household Applications

General Information				
Filler / Reinforcement		Long Glass Fiber,60% Filler by Weight		
Features		Aromatic		
		Good Flow		
		Good Mold Release		
		High Heat Resistance		
Uses		Appliance Components		
		Automotive Applications		
		Automotive Electronics		
		Automotive Exterior Parts		
		Automotive Interior Parts		
		Connectors		
		Electrical/Electronic Applications		
		Engineering Parts		
		Household Goods		
		Hydraulic Applications		
		Lighting Applications		
		Pneumatic Applications		
		Power/Other Tools		
Appearance		Black		
Forms		Granules		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.69	--	g/cm³	ISO 1183

Molding Shrinkage				ISO 294-4
Across Flow	0.20	--	%	
Flow	0.10	--	%	
Water Absorption				ISO 62
Saturation, 23°C	3.5	--	%	
Equilibrium, 23°C, 50% RH	1.2	--	%	
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness	310	285	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	22500	21000	MPa	ISO 527-2
Tensile Stress (Break)	290	250	MPa	ISO 527-2
Tensile Strain (Break)	2.1	2.1	%	ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	40	40	kJ/m ²	
23°C	40	40	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	90	90	kJ/m ²	
23°C	110	110	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
1.8 MPa, Unannealed	255	--	°C	ISO 75-2/A
8.0 MPa, Unannealed	225	--	°C	ISO 75-2/C
Maximum Use Temperature				Internal Method
Long Term	100 to 120	--	°C	
Short Term	220	--	°C	
ISO Type	PA66+PA6I/X, MH, 14-220N, GF60			ISO 1874
Melting Temperature ¹	260	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow	2.0E-5	--	cm/cm/°C	
Transverse	4.0E-5	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	--	1.0E+13	ohms	IEC 60093
Volume Resistivity	1.0E+12	1.0E+12	ohms·cm	IEC 60093
Electric Strength	33	33	kV/mm	IEC 60243-1
Comparative Tracking Index	--	600	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method

Flammability Classification (0.800 mm)	HB	--	IEC 60695-11-10, -20
---	----	----	----------------------

NOTE

- 10°C/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

