OnFlex[™] S KG 80A-3E2020

Thermoplastic Elastomer

PolyOne Corporation

Message:

OnFlex[™]-S KG thermoplastic elastomer polymer is mixed with hydrogenated styrene block copolymer. This series of polymers has good compatibility and can provide excellent adhesion to polyamide polymer materials, such as PA6, PA6.6, PA11 and PA12. OnFlex-S KG polymer can be processed by 2K molding or multiple injection molding, plug-in molding or co-extrusion. In addition, OnFlex[™]-S KG polymer has good processability, good cost performance, wide hardness range, good coloring and mechanical properties.

General Information						
Features	Good adhesion					
	General					
Uses	overmolding					
	Power/other tools					
	Industrial application					
	Application in Automobile Field					
	Consumer goods application field					
RoHS Compliance	RoHS compliance	RoHS compliance				
Forms	Particle	Particle				
Processing Method	Multiple injection molding	Multiple injection molding				
	Co-extrusion molding	Co-extrusion molding				
Physical	Nominal Value	Unit	Test Method			
Density	1.13	g/cm³	ISO 1183			
Hardness	Nominal Value	Unit	Test Method			
Durometer Hardness (Shore A)	80		ISO 868			
Elastomers	Nominal Value	Unit	Test Method			
Tensile Stress (100% Strain)	3.50	MPa	ISO 37			
Tensile Stress (Break)	4.90	MPa	ISO 37			
Tensile Elongation (Break)	290	%	ISO 37			
Tear Strength	29	kN/m	ISO 34-1			
Compression Set			ISO 815			
23°C, 72 hr	35	%	ISO 815			
70°C, 22 hr	66	%	ISO 815			
100°C, 22 hr	84	%	ISO 815			
Additional Information	Nominal Value	Nominal Value				
General Material Type	Styrene thermoplastic elast	Styrene thermoplastic elastomers (TES)				
各项属性值是采用注射模制基板测量得	出.					
Injection	Nominal Value	Unit				

Drying Temperature	100	°C	
Drying Time	2.0	hr	
Processing (Melt) Temp	200 - 260	°C	
Mold Temperature	30.0 - 50.0	°C	
Injection Rate	Moderate		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

