

Tecnoprene® T60K4 NERO900

Polypropylene Homopolymer

SO.F.TER. SPA

Message:

Low fluidity polypropylene homopolymer reinforced with 20% chemically coupled glass fiber

General Information			
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Features	Chemically Coupled		
	Homopolymer		
	Low Flow		
Uses	Automotive Applications		
Agency Ratings	EC 1907/2006 (REACH)		
Appearance	Black		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	1.0	g/10 min	ASTM D1238
Molding Shrinkage	0.70	%	Internal Method
Water Absorption (Saturation, 23°C)	0.020	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	4100	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	150	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	140	°C	ASTM D648
Vicat Softening Temperature	125	°C	ASTM D1525 ¹
Flammability	Nominal Value	Test Method	
Flame Rating (3.20 mm)	HB	UL 94	
NOTE			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

