

PermaStat® 300 FR A

Polycarbonate

RTP Company

Message:

ESD Protection - Permanently Anti-static - Flame Retardant

General Information			
UL YellowCard	E84658-251431		
Features	Electrostatic discharge protection		
	Antistatic property		
	Flame retardancy		
RoHS Compliance	Contact manufacturer		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.30	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	0.50 - 0.70	%	ASTM D955
Moisture Content	0.020	%	
Static Decay		sec	FTMS 101C 4046.1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2760	MPa	ASTM D638
Tensile Strength	51.7	MPa	ASTM D638
Tensile Elongation (Yield)	6.0 - 8.0	%	ASTM D638
Flexural Modulus	2760	MPa	ASTM D790
Flexural Strength	86.2	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	190	J/m	ASTM D256
Unnotched Izod Impact (3.20 mm)	1300	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	124	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+10 - 1.0E+11	ohms	ASTM D257
Volume Resistivity	1.0E+8 - 1.0E+10	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	4.0	hr	
Dew Point	-28.9	°C	

Processing (Melt) Temp	221 - 243	°C
Mold Temperature	65.6 - 121	°C
Injection Pressure	41.4 - 68.9	MPa

Injection instructions

Do not exceed 520 °F (270 °C) melt temperature.Desiccant Type Dryer Required.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

