## Daelim Po1y® LD-08A

Low Density Polyethylene
DAELIM INDUSTRIAL CO., LTD.

## Message:

Daelim Po1y®LD-08A is a low density polyethylene product. It is available in the Asia-Pacific region. Daelim Po1y®LD-08A application areas include film and food contact applications.

Features include:

Good sealing performance

Good toughness

Impact resistance

General Information			
Features	Impact resistance, high		
	Good heat sealability		
	Good toughness		
Uses	Films		
Agency Ratings	ASTM D 1248, I, Class A, Cat. 4		
	FDA 21 CFR 177.1520		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Density	0.922	g/cm³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/			
kg)	0.50	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	200	μm	
Tensile Strength			ASTM D882
MD: Fracture	22.6	MPa	ASTM D882
TD: Fracture	21.6	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Fracture	440	%	ASTM D882
TD: Fracture	470	%	ASTM D882
Dart Drop Impact	650	g	ASTM D1709
Elmendorf Tear Strength			ASTM D1922
MD	150	g	ASTM D1922
TD	150	g	ASTM D1922
Optical	Nominal Value	Unit	Test Method
Haze	17	%	ASTM D1003
Additional Information			
Tear Strength, MD, ASTM D-1004: 1	00kg/cmTear Strength, TD, ASTM D-1	004: 100kg/cm	
Injection	Nominal Value	Unit	

Processing (Melt) Temp

160 - 190

°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

